5

Patent Claims

- Recording material having a dimensionally stable, two-dimensional support and a negative-working, radiation-sensitive layer which comprises a diazonium salt and a polymeric binder, characterized in that the layer comprises a sulphobetaine.
- 2. Recording material according to Claim 1,
 10 characterized in that the radiation-sensitive layer
 comprises a combination of a polymerizable monomer
 or oligomer and a photopolymerization initiator.
- 3. Recording material according to Claim 1 or 2, characterized in that the sulphobetaine conforms to the following formula I

$$R^{2} \longrightarrow \begin{pmatrix} R^{1} \\ | \\ N^{+} \longrightarrow R^{4} \longrightarrow SO_{3} \end{pmatrix}$$
 (I)

in which

identical R^1 to R^3 different are or and substituted or unsubstituted and/or monoor polyunsaturated, acyclic or isocyclic hydrocarbon radicals having from 1 to 16 carbon atoms, in which one or methylene groups may be replaced by -O-, -NH-, -CO-NH- and/or -O-CO-NHgroups, and, in the case of the acyclic radicals, each two thereof may be linked to one another to form a saturated or unsaturated ring, and

 R^4 is a substituted or unsubstituted (C_1 - C_6)alkanediyl group.

30

20

25

35

15

- 4. Recording \setminus material according to Claim 3, characterized in that at least one of the radicals R^1 to R^3 is a methyl radical.
- 5 5. Recording material according to Claim 3 or 4, characterized in that two of the radicals R¹ to R³ are linked to one another with formation of a five-to seven-membered ring, preferably a morpholinium or pyridinium ring.

10 6. Recording material _according to Claim 3. in that R^4 the radical characterized unsubstituted substituted or ethane-1,2-diyl, propane-1,3-diyl or butane-1,4-diyl radical.

7. Recording material according to one or more of Claims 1 to 6, characterized in that the proportion of the sulphobetaines is from 1 to 15% by weight, preferably from 2 to 10% by weight, in each case based on the total weight of the non-volatile constituents of the radiation-sensitive layer.

- 8. Recording material according to one or more of Claims 1 to 7, characterized in that the radiation-sensitive layer has been coloured using dyes and/or pigments.
- 9. Recording material according to one or more of Claims 1 to 8, characterized in that the diazonium salt is a condensation product of an aromatic diazonium salt.
- 10. Recording material according to one or more of Claims 1 to 9, characterized in that the weight of the dried radiation-sensitive layer is from 0.3 to $3.0~{\rm g/m^2}$, preferably from 0.5 to $2.0~{\rm g/m^2}$, particularly preferably from 0.6 to 1.6 ${\rm g/m^2}$.

- 11. Recording material according to one or more of Claims 1 to 10, characterized in that it is pigmented or matted.
- 5 12. Recording material according to one or more of Claims 1 to 11, characterized in that the support is a plate, a film, a foil or a band of metal, plastic or a plastic/metal laminate.
- according 13. Recording material to Claim 12, 10 characterized in that / the support consists of aluminium or an aluminium Alloy, where at least one support of the has preferably mechanically, chemically and/or electrochemically roughened, if desired also anodically oxidized 15 and/or chemically/aftertreated.
- 14. Recording material according to one or more of Claims 1 to 13, characterized in that the support has been provided with a back coating of polymeric materials.
- 15. Process for the production of a printing plate for offset printing, characterized in that a recording material according to one or more of Claims 1 to 14 is exposed imagewise and subsequently developed using an aqueous-alkaline developer.

30

-.-.